







ALPHA

version 27/06/2019
replaces

Manufacturing type	Herstellungsart	Mode fabrication	Productie methode		needlepunch
Construction	Struktur	Structure	Structuur		rib
Pile composition	Polmateriaal	Couche d'usure	Poolsamenstelling		100% PP
Dye method	Farbgestaltung	Coloration	Kleurverwerking		solution dyed
Backing	Rücken	Dossier	Rug		latex
Pile weight	Poleinsatzgewicht	Poids de velour	Poolgewicht	ISO 2424	g/m2 875 (+/-)
Total weight	Gesamtgewicht	Poids total	Totaal gewicht	ISO 8543	g/m2 950 (+/-)
Pile height	Polhöhe	Hauteur du velours	Poolhoogte	ISO 1766	mm 6,0 (+/-)
Size	Abmessung	Dimension	Afmeting		cm 200 / 400
Classification	Klassifikation	Classement	Gebruiksklasse	EN 1307	31
Comfort rating	Komfortklasse	Classement confort	Comfort klasse	EN 1307	LC 2
Castor chair	Stuhlleneignung	Chaise à roulettes	Rolstoelgeschikt	EN 985	
Stair suitability	Treppeneignung	Escaliers	Trappengeschikt	EN 1963	
Fire resistance	Brennverhalten	Comportement feu	Brandgedrag	EN 13501-1	Efl (Cfl-S1 on request)
Permanent antistatic	Permanent Antistatisch	Antistatique permanent	Permanent antistatisch	ISO 6356	kV ≤ 2,0
Transversal resistance	Durchgangswiderstand	Résistance transversale	Doorgangsweerstand	ISO 10965	Ω ≥ 10¹⁰
Thermal resistance	Wärmedurchlaßwiderstand	Résistance thermique	Warmtedoorlaatweerstand	ISO 8302	m2/K/W
Sound absorption	Schallabsorptionsgrad	Absorption phonique	Geluidsabsorptie	ISO 354	α_w
Impact sound reduction	Trittschallverbesserungsmaß	Isolation phonique	Geluidsisolatie	ISO 10140	ΔL_w
				ISO 10140	ΔL 27 dB (1000 Hz)
Colour fastness light	Lichtechtheit	Solidité à la lumière	Lichtechtheid	ISO 105 B02	≥ 5
Rubbing fastness	Reibechtheit	Solidité au frottement	Wrijftechtheid	ISO 105 X12	≥ 5



 16 EN 14041 DOP 000550L-001	 
	  
EN 1307 for use as floorcovering in buildings (EN 14041) accordings to the manufacturer's specification	

These technical details are approximate. Complete specification details and associated certificates together with tolerances applying to the above can be provided upon request, if available. We reserve the right to alter specifications without notice. Due to the method of manufacture, perfect pattern/colour matching cannot be guaranteed. Shading/pile reversal might occur in cut pile carpets, without affecting overall quality and suitability. It is not considered as a manufacturing fault.