






VINTAGE COLLECTION

Felina - Ferrera - Firenze

version 10/12/2019
replaces 4/09/2019

Manufacturing type	Herstellungsart	Mode fabrication	Productie methode			
Construction	Struktur	Structure	Structuur			tufted 1/10"
Pile composition	Polmaterial	Couche d'usure	Poolsamenstelling			structured loop pile
Dye method	Farbgestaltung	Coloration	Kleurverwerking			100% PA - Econyl®
Primary backing	Trägermaterial	Premier dossier	Tuftdoek			chromojet
Secondary backing	Rückenausrüstung	Dossier	Rug			non-woven
Pile weight	Poleinsatzgewicht	Poids de velour	Poolgewicht	ISO 2424	g/m2	900 (+/-)
Total weight	Gesamtgewicht	Poids total	Totaal gewicht	ISO 8543	g/m2	1.950 (+/-)
Pile height	Polhöhe	Hauteur du velours	Poolhoogte	ISO 1766	mm	5,0 (+/-)
Total height	Gesamtdicke	Epaisseur totale	Totale dikte	ISO 1765	mm	6,5 (+/-)
Tuft density	Noppenzahl	Nombre de touffes	Aantal punten	ISO 1763	/m2	191.000 (+/-)
Size	Abmessung	Dimension	Afmeting		cm	400
Classification	Klassifikation	Classement	Gebriuksklasse	EN 1307		33 heavy commercial
Comfort rating	Komfortklasse	Classement confort	Comfort klasse	EN 1307		LC 2
Castor chair	Stuhlrolleneignung	Chaise à roulettes	Rolstoelgeschikt	EN 985		A intensive
Stair suitability	Treppeneignung	Escaliers	Trappengeschikt	EN 1963		A intensive
Fire resistance	Brennverhalten	Comportement feu	Brandgedrag	EN 13501-1		Cfl-s1 glued
Permanent antistatic	Permanent Antistatisch	Antistatique permanent	Permanent antistatisch	ISO 6356	kV	≤ 2,0
Transversal resistance	Durchgangswiderstand	Résistance transversale	Doorgangsweerstand	ISO 10965	Ω	> 10¹⁰
Thermal resistance	Wärmedurchlaßwiderstand	Résistance thermique	Warmtedoorlaatweerstand	ISO 8302	m2/K/W	
Sound absorption	Schallabsorptionsgrad	Absorption phonique	Geluidsabsorptie	ISO 354	α _w	
Impact sound reduction	Trittschallverbesserungsmaß	Isolation phonique	Geluidsisolatie	ISO 10140	ΔL _w	23 dB
				ISO 10140	ΔL	(1000 Hz)
Colour fastness light	Lichtechtheit	Solidité à la lumière	Lichtechtheid	ISO 105 B02		≥ 5-6
Rubbing fastness	Reibechtheit	Solidité au frottement	Wrijftechtheid	ISO 105 X12		≥ 3-4
				DIBt Nr.		Z-156.601-1010



 18 EN 14041 DOP 600599598A-001	 Cfl-s1
	 DS
	 DL PCP
	 NA HCHO
EN 1307 for use as floorcovering in buildings (EN 14041) accordings to the manufacturer's specification	



TÜV Emission testing

Results comply with emission threshold of

- AgBB - Germany
- Belgian VOC regulation
- BREEAM Exemplary level
- French VOC regulation
- LEED V4 (outside North America)



Made with 100% Regenerated Nylon

ECONYL®



special design / colour : minimum 400m2

ALSO AVAILABLE



These technical details are approximate. Complete specification details and associated certificates together with tolerances applying to the above can be provided upon request, if available. We reserve the right to alter specifications without notice. Due to the method of manufacture, perfect pattern/colour matching cannot be guaranteed.

Shading/pile reversal might occur in cut pile carpets, without affecting overall quality and suitability. It is not considered as a manufacturing fault.